



CSI Code: 07920

No. 790

JULY 2004  
(Supersedes January 2004)

## CERA-ROD™

Non-Gassing, Heat-Resistant Backer Rod

### DESCRIPTION

CERA-ROD is a round, flexible, continuous-length, non-absorbent, non-gassing, non-staining, and non-shrinking material extruded from a cross-linked polyethylene. Compression/deflection is approximately 8 psi (55.2 KPa) at 25% deflection.

### USES

CERA-ROD is used in joints or large cracks in Portland cement or asphalt concrete. It provides the correct sealant reservoir configuration, controls joint depth and prevents sealant run-out through the bottom of the joint. CERA-ROD also acts as a bond-breaker to prevent bottom side sealant adhesion.

### PACKAGING

Easy to identify carton and product on the job site

Cartons weigh 11 lbs. (4.99 kg) each, except the 1-1/2" and 2" (38.1 and 50.8mm) sizes that weigh 30 lbs. (13.61 kg) each.

### SPECIFICATION

ASTM D 5249, Type I

### COLOR

Red

### FEATURES AND BENEFITS

- Works equally well with concrete or asphalt surfaces
- Use with hot-applied joint sealants...will not melt, shrink, evaporate or stain
- Retains its original diameter and is non-gassing when exposed to high sealant temperatures
- Prevents run-out through voids or bottom of the joint...saves sealant material
- Acts as a bond breaker to stop sealant adhesion to the bottom side of the joint
- Fast and easy to apply

### STANDARD SIZES

Rod Diameter	Lineal Feet per Carton	Lineal Meters per Carton
3/8" (9.5mm)	4,200	1,280.16
1/2" (12.7mm)	2,500	762.00
5/8" (15.9mm)	1,500	472.44
7/8" (22.2mm)	850	259.08
1" (25.4mm)	600	182.88
1-1/4" (31.8mm)	400	121.92
1-1/2" (38.1mm)	1050	320.04
2" (50.8mm)	600	182.88

*CONTINUED ON REVERSE SIDE...*

### Application Tools



Three-Wheeled Roller



Single-Wheeled Roller

### PRECAUTIONS

Read and follow application information and Material Safety Data Sheet Information.

**FOR THE MOST CURRENT PRODUCT INFORMATION, VISIT OUR WEBSITE:  
[www.wrmeadows.com](http://www.wrmeadows.com)**

### APPLICATION

**Crack and Joint Preparation...**Remove all dirt and foreign matter.

**Method of Application...**Install CERA-ROD with a single-wheeled or three-wheeled roller, depending on application. Avoid stretching or puncturing the material. CERA-ROD needs to be held in compression to work effectively. The diameter of the rod should be 1/8" larger than the width of the joint for joint widths up to 3/4"; for joints 3/4" and larger, add 1/4" to diameter rod selection. Applications for all hot-applied joint sealants from W. R. MEADOWS can follow immediately.



### LIMITED WARRANTY

"W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order." Read complete warranty. Copy furnished upon request.

### Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.