



CSI Code: 03 62 13

NO. 389

MARCH 2006
(Supersedes December 2005)

MEADOW-PLUG™

One Component, Super Fast Setting, Hydraulic Repair Mortar

DESCRIPTION

MEADOW-PLUG is a specially blended, extremely fast setting, hydraulic cement product designed to instantly stop running water or fluid seepage in concrete or masonry structures. This single component, high strength repair mortar permanently plugs non-moving cracks, joints and voids.

USES

Once mixed with water to a putty-like consistency, MEADOW-PLUG may be hand formed to quickly stop active fluid leaks in basements, tunnels, swimming pools, sewers, non-potable water tanks, voids around pipes and wall tie holes. It seals construction joints between floors and walls. MEADOW-PLUG is versatile enough for either vertical or horizontal applications; below, above or on grade.

Its controlled expansion formulation permanently holds the repair in place on exterior, interior, even, underwater installations.

PACKAGING

50 lb. (22.7 kg) Pails
8 lb. (3.6 kg) Tubs

FEATURES/BENEFITS

- Fast initial set / Stops liquid flow immediately.
- Expands as it sets / Forms a permanent water stop.
- Mixes with water only / Easy to use.
- Horizontal, vertical, interior, exterior / Highly versatile.
- Above grade, below grade, underwater / Multi-purpose.
- Non-metallic, non-corrosive / Will not stain.
- May be topcoated within one hour / Saves time.
- Good sulfate resistance / Suitable for wastewater and sewer applications.

TECHNICAL DATA*

Compressive strength (Per ASTM C 109) at:

15 min.	850 psi (5.86 MPa)
1 hour	1225 psi (8.44 MPa)
1 day	2650 psi (18.27 MPa)
28 days	6000 psi (41.38 MPa)

Set time (Per ASTM C 191)

Initial: 2 minutes
Final: 3 minutes

*All technical data is typical information, but may vary due to testing methods, conditions and operators.

ADDITIONAL RESTORATION PRODUCTS FROM W. R. MEADOWS CAN BE FOUND BY VISITING OUR WEBSITE:

www.wrmeadows.com

CONTINUED ON REVERSE SIDE...

SURFACE PREPARATION

Cut or notch out the crack, joint, or void to a minimum dimension of 3/4"x 3/4". To ensure proper mechanical lock, the bottom of the newly notched opening should be wider than the top. (Avoid "V" type notches or cuts.) Prepare surface in accordance with ICRI Technical Guide No. 03730. Substrate must be structurally sound and free of grease, oil, dirt, or any other contaminants that can adversely affect the bond. If the crack to be repaired is dry at the time of application, substrate must be dust free, then saturated, surface dry (SSD).

MIXING AND PLACEMENT

Mix MEADOW-PLUG with enough potable water to form a thick putty consistency (approximately a 4:1 ratio by volume). Do not mix more MEADOW-PLUG than can be placed in one minute. Force MEADOW-PLUG directly into prepared crack and hold in place, maintaining pressure until material hardens. Avoid overworking the material. Just prior to final set, MEADOW-PLUG may be "shaved" to match the profile of the area surrounding the patch. If repairing a dry crack, wet cure immediately for at least fifteen minutes or until set is fully achieved. **Do not use on any moving joints.**

HEALTH AND SAFETY

Refer to Material Safety Data Sheet for complete health and safety information.

FOR BEST PERFORMANCE:

- MEADOW-PLUG is recommended for concrete, masonry and block repairs only.
- Do not apply below 40° F (4° C) or above 90° F (32° C) or when rain is imminent.

- Protect from freezing for a minimum of 24 hours.
- Do not bridge moving cracks. Extend existing control and expansion joints through MEADOW-PLUG.
- Do not add any admixtures.
- Exceeding liquid requirements shall result in reduced physical properties.
- Realize that set time will decrease as the product, air, substrate and mixing liquid temperature increases and will increase as the temperature decreases.
- Protect from conditions that may cause early water loss: windy conditions, low humidity, high temperature and direct sunlight. Early water loss is exasperated in thin applications.
- Failure to follow industry standard practices may result in decreased material performance.
- Proper application is the responsibility of the user. Field visits by W. R. MEADOWS personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the jobsite.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.