



PRODUCT DATA SHEET

1215 DT Iowa/Nebraska DOT

PROPERTY	TEST METHOD	MARV
Tensile Strength (Grab)	ASTM D-4632	175/130
Elongation	ASTM D-4632	8%
Puncture	ASTM D-4833	65 lbs
Mullen Burst	ASTM D-3786	275 psi
Trapezoidal Tear	ASTM D-4533	65 lbs
UV Resistance	ASTM D-4355	80% AFTER 500 HRS
Apparent Opening Size (AOS)	ASTM D-4751	30 US Std. Sieve
Percent Open Area (POA)	CW-02215 Mod.	
Permittivity	ASTM D-4491	1.0 sec ⁻¹
Water Flow Rate	ASTM D-4491	90 gpm/ft ²
Roll Sizes		36", 42"

The property values listed above are subject to change without notice.

Willacoochee Industrial Fabrics
Quality at Competitive Prices.

769 West Main Street
PO Box 599
Willacoochee, GA 31650

PH: 912-534-5757
FAX: 912-534-5533
www.winfabusa.com